




COMPRESSION BONDED NEODYMIUM MAGNETS: N-88



Grade	$(BH)_{max}$		$B_r$		$H_c$		$H_{ci}$		$B_d$	$H_d$	$T_c$	$D$
	MGOe	$kJ/m^3$	kG	mT	kOe	kA/m	kOe	kA/m	%/°C	%/°C	°C	$g/cm^3$
N-88	7.5-8.5	60.9-69.1	6.3	630	5.3	424	10.0	800	-0.10	-0.40	140	5.8-6.0

ALL SPECIFICATIONS ARE SUBJECT TO CHANGE WITHOUT NOTICE